International Journal of Scientific Research & Engineering Trends
Volume 5, Issue 6, Nov-Dec-2019, ISSN (Online): 2395-566X

Manufacturing and Testing the Surface Integrity of The Bimetallic Pistons and Its Significance

Research Scholar Sumeet Hangargi, Professor G. R. Selokar (Supervision)
Department of Mechanical Engineering,
Sri Satya Sai University of Technology & Medical Sciences
Sehore, Bhopal, M.P, India,
sumeet.cmrec@gmail.com, selokar1960dr@gmail.com

***Abstract*- The bond integrity after machining is primarily related to the magnitude of the cutting forces during machining and thus the objective of the paper is to obtain optimal cutting parameters in turning of such pistons. In addition, any machining process should also satisfy surface finish requirements. A Taguchi analysis of the influence of cutting speed, feed, and depth of cut on cutting force were conducted and the extent of debonding and the surface finish was measured independently after machining to ensure that this minimum cutting force condition fully satisfied all the product requirements Those parameters yielding minimum cutting forces were identified as minimal cutting force parameters, so numerical simulation and experiments were carried out on these parameters. After machining, the intermediate bonding between metallic regions was studied using ultrasonic testing. Bimetallic machining is successfully simulated, and its potential is readily applied to an industrially important component.**

Keywords: Bimetallic piston, Depth, Feed, Speed, Surface roughness,Al,CI etc.

I.INTRODUCTION

The bimetallic car segment comprises of an aluminum–silicon composite fortified with an iron based addition. In perspective on diminishing the heaviness of the segment and for better mechanical properties it was fabricated by gravity kick the bucket throwing technique.

The output data of the developed mathematical model is compared with the experimental results and also to predict the cutting force at different machining condition without performing real time experiment. The results of Taguchi's robust design concept are compared with the results obtained from the non conventional optimization technique called Genetic Algorithm (GA) which is performed through the MATLAB.

The friction coefficient between titanium alloy and the tools that cut it is large, and the friction speed for titanium alloy chips is particularly high along the rake face. Severe friction causes tool wear, and results in poor surface quality. In the face of this, a large number of studies have found that adding a micro-texture to the tool's surface can bring about good anti-friction and anti-adhesion effects, improve wear resistance, and improve the quality of the machined surface.

Bimetallic pistons are fabricated through gravity kick the bucket throwing, by strengthening dim give iron a role as an addition in the aluminum composite. The graphite particles in dim, pliant and flexible irons are in charge of the free-machining attributes of the cast iron and their better machinability when thought about than steels. Inside the cast irons, graphite morphology assumes a significant job in machinability, with the graphite chips found in dim iron giving predominant machining attributes. While the graphite particles impact cutting power and surface completion, the grid is the essential determinant of hardware life.

The optimum machining conditions are obtained through Taguchi's robust design technique. Cutting forces are measured for the air quenched with 1½ minutes dipped in condition piston and is considered for study.

II. LITERATURE REVIEW

1. The first is a steel aisi 1045 with a side of the equator shape, whose geometry is basic. The subsequent one is a steel din 1.2379 section (64 hrc), with progressively complex highlights. The surface quality was assessed for both shining approaches, acquiring noteworthy enhancements for the surface unpleasantness and hardness. The fundamental general end is that ball shining diminishes the unpleasantness without punishing the assembling time or surface honesty, and in this manner, it is reasonable for complex surfaces.

2. *The m*odel is utilized as the seed for an estimation module, in light of strong displaying, to acquire the surface unpleasantness and geology by applying the cutting power divider compensation balance, utilizing the intensity of pc helped fabricating (cam) strong

© 2019 IJSRET

modelers for the last geography definition. This thought exploits the great precision of current strong modelers in correlation with the z-map geological methodology for getting the shaper workpiece commitment (cwe) at each toolpath step. A few flank processing tests were done to approve the reenactments. The outcomes exhibited a critical degree of exactness to foresee shape blunders.

The graphite particles in dim, pliant and flexible irons are in charge of the free-machining attributes of the cast iron and their better machinability when thought about than steels. Bimetallic pistons are fabricated through gravity kick the bucket throwing, by strengthening dim give iron a role as an addition in the aluminum composite. Inside the cast irons, graphite morphology assumes a significant job in machinability, with the graphite chips found in dim iron giving predominant machining attributes. While the graphite particles impact cutting power and surface completion, the grid is the essential determinant of hardware life.

III. RESEARCH METHODOLOGY

1. Heat treatment

The cast pistons are exposed to heat treatment at different temperature plans. The heat treatment procedures did are

- Air extinguished
- Water extinguished techniques. To have correlation as cast pistons are utilized.

2. Various dipping conditions

The plunging time of supplement assumes imperative job in holding henceforth examinations are made on the pistons with 1½ minutes, 2 minutes, 3 minutes, 4 minutes and 5 minutes plunging conditions. Subsequent to making the piston, it is sliced into example and exposed to heat treatment at various temperature with and without hardening process. The mechanical properties are assessed through shear quality test by utilizing widespread testing machine. Hardness testing is done at aluminum and cast iron bits through Brinell hardness analyzer.

3. Machining

To make the piston into close to net shape, it is to be machined with a target of estimating cutting power at various machining parameters (speed, feed, and profundity of cut) without irritating holding nature. In the bimetallic area, a solitary device is presented for machining both the metals as opposed to utilizing two distinct devices.

4. Surface Integrity

A scientific model was created so as to appraise the cutting power at various information parameters by utilizing SYSTAT programming and the anticipated yield was thought about against the exploratory qualities. A non conventional enhancement system GA is utilized to improve the machining parameters. The outcomes acquired through GA are contrasted and Taguchi strong plan yield.

5. Procedure & Statistical Analysis

Destinations of the examination, explore theory and research plan. This exploration has structured dependent on spellbinding investigation as it expects to recognize and expand the targets of work.



Fig 1 Flow Chart Of Research Work.

Fig 2 Ultrasonic Piston Bond Tester

6. Tool Wear

CBN instrument isn't for the most part prescribed for machining of aluminum combinations because of the poor

surface completion. Anyway by utilizing improved parameters, surface completion can be reestablished.

Table 1 Surface Roughness Values.

Experimental Run	Surface Roughness ( )
1.	1.700
2.	2.510
3.	3.470
4.	1.780
5.	7.570
6.	3.470
7.	1.700
8.	2.560
9.	3.470



Fig 3Surface roughness measurement.



Fig 4 Micrograph of new tool.



Fig 5 Micrograph of crater wear.



Fig 6 Crater wear at x150.



Fig 7 Typical Micrograph Of As Cast Piston.



Fig 8 Typical Micrograph Of As Cast Piston.

7. X Ray Diffraction

There are nine types of ternary mixes in Al-Si and Fe frame work Regularly X Ray Diffraction study is utilized to break down the stage present with data on cross section type direction .The stages present in Al-Si and Fe framework can be comprehended from the ternary stage

© 2019 IJSRET

outline .Fe Al2, Fe2 Al5 and Fe Al3 are the conceivable middle of the road stages in Fe-Al framework.

Table 2 Al-Fe-Si Crystal Structure.

Phase	% Composition		
	Al	Fe	Si
Al2Fe3Si3	25.0	37.5	37.5
Al2FeSi	50.0	25.0	25.0
Al2.7FeSi2.3	45.0	16.7	38.3
Al15Fe6Si5	57.7	23.1	19.2
Al4.5FeSi	69.2	15.4	15.4
Al63.5Fe20.5Si16	93.5	20.5	16.0
Al6Fe4Si6	37.5	25.0	37.5
Al2Fe3Si4	22.2	33.3	44.4
Al4Fe1.7Si	59.7	25.4	14.9

8. Hardness Survey

Al-CI (treated and untreated) are considered through hardness review. Hardness data was taken utilizing Brinell hardness analyzer at five distinct areas on the example at either side.

The hardness variety for as cast, air extinguished and water extinguished piston of aluminum and cast iron sides are given the proportional Vickers hardness (HV).



Fig 9 Hardness Chart Of Aluminium.



Fig 10 Hardness chart of Cast iron.



Fig 11 Surface Roughness Measurement Facility.



Fig 12 Typical Application Of Load On Piston.

IV. RESULTS ANALYSIS

Solidified carbide instruments are regularly utilized for machining the cast iron piece of the piston. Henceforth, to machine the holding area, two various types of instruments are utilized. Be that as it may, this prompts a continuous difference in apparatus and machining parameters. This outcomes in decrease of efficiency. Time study was started to watch the absolute time required for machining a piston.

- Machining time required for holding zone of every piston is of 26 seconds.
- Identification of important decision variables, which control and improve the performance of the product or process.
- Robustness decreases the variety in parts by diminishing the impacts of wild variety.
- Utilization of Taguchi's symmetrical exhibit is progressively worthwhile in light of the fact that it decreases the quantity of examinations without losing the quality.
- This specific cylinder is separated into three sub parts which are cylinder crown, cylinder skirt and cylinder stick.

© 2019 IJSRET

By utilizing treated steel, cast-iron, aluminum compound, aluminum oxide (Al2O3) and silicon carbide (Sic). By taking 4 unique cases with single material and 4 distinct cases with various material blends by utilizing ANSYS reports have been created.

Table 3 Experimental Result

Experimental Run	Speed (m/min)	Feed (mm/rev)	Depth of cut (mm)	Mean Cutting force at bonding region (N)
1.	452	0.15	0.15	42
2.	452	0.20	0.20	55
3.	452	0.25	0.25	82
4.	482	0.15	0.20	60
5.	482	0.20	0.25	85
6.	482	0.25	0.15	58
7.	512	0.15	0.25	53
8.	512	0.20	0.15	39
9.	512	0.25	0.20	76



Fig 13 Pareto Chart For 1½ Minutes Dipped Insert Piston.



Fig 14 Force Comparison On Different Time Dipped Insert Piston.

V. CONCLUSIONS

There is no huge change on cutting power regardless of whether the plunged time is stretched out past 2 minutes. To the extent the holding nature is concerned, the 2 minutes plunged in condition withstands more power and consequently it is recognized as better dunked in condition. The equivalent is additionally confirmed with push out test. Low speed, high feed and bigger profundity of cut outcome the most elevated cutting power.

Relapse investigation completed on the symmetrical test outcomes built up expectation models for work solidifying and surface unpleasantness. The dependability of these models was affirmed by correlation between qualities from the trials and the qualities anticipated by the models. The surface integrity of the machined pistons was evaluated using surface roughness and bond-checking tests. The machined pistons exhibited good surface integrity for the chosen level of parameters.

REFERENCES

[1] Fang, Y.F.; Tee, K.F. Effects on Surface Integrity of Ti6Al4V in High Speed Milling. Key Eng. Mater. 2017, 737, 156–161. [CrossRef]
[2] Cui, Y. Research on the Surface Quality of Titanium Alloy with Micru-textured Ball-end Milling Cutter. Master's Thesis, Harbin University of Science and Technology, Harbin, China, March 2016.
[3] Fu, Y.-H.; Xiao, K.-L.; Hua, X.-J.; Yuan, Z.C.; Yang, Y.G. Cut-ting Trial and Performance Analysis of Surface Micro-grooves Turning Tools. China Surf. Eng. 2013, 6, 106–111.
[4] Koshy, P.; Tovey, J. Performance of electrical discharge textured cutting tools. CIRP Ann. 2011, 60, 153–156. [CrossRef] 4. Xie, J.; Luo, M.J.; He, J.L.; Liu, X.R.; Tan, T.W. Micro-grinding of micro-groove array on tool rake surface for dry cutting of titanium alloy. Int. J. Precis. Eng. Manuf. 2012, 13, 1845–1852. [CrossRef]
[5] Benardos and Vosniakos, (2002), 'Prediction of surface roughness in CNC face milling using neural network and Taguchi Design of experiments' Robotics and computer integrated manufacturing Vol. 18, pp343-354.
[6] Budinski (2001) 'Engineering materials: Properties and Selection' Prentice hall of India (P) Ltd, New Delhi.
[7] Cole G.S. and Sherman A.M. (1995) 'Light weight aluminum alloy for automotive application' Material Characterization. Vol. 35, pp. 3-9.
[8] B. Srinivasulu ,Joining of Al(6061-T6) and Brass(IS319) by using EN19 Circular Profile Tool through Friction Stir Spot Welding, International Research Journal of Engineering and Technology (IRJET), e-ISSN: 2395-0056, p-ISSN: 2395-0072.
[9] Palanikumar, K. and Davim, J. P., "Mathematical model to predict tool wear on the machining of glass fibre reinforced plastic composites," Materials & Design, Vol. 28, Issue 7, pp. 2008-2014, 2007.
[10] Sharma, V. S., Dhiman, S., Sehgal, R. and Sharma, S. K., "Assessment and Optimization of Cutting Parameters while Turning AISI 52100 Steel," International Journal of Precision Engineering and Manufacturing, Vol. 9, No. 2, pp. 54-62, 2008.
[11] Saravanan, R., Asokan, P. and Sachithanandam, M., "Comparative analysis of conventional and non conventional optimization techniques for CNC

© 2019 IJSRET

turning process," International Journal of Advanced Manufacturing Technology, Vol. 17, No. 7, pp. 471-476, 2001.

© 2019 IJSRET